

Demagnetization Curves of Cast AlNiCo Magnets

Tri-AlNiCo-5

		SI	CGS
Remanence	Br	$\geq 1.25 \text{ T}$	$\geq 12.5 \text{ KG}_s$
Coercivity	Hcb	$\geq 52.0 \text{ kA/m}$	$\geq 650 \text{ Oe}$
Maximum Energy Product	(BH)max	$\geq 44.0 \text{ kJ/m}^3$	$\geq 5.50 \text{ MGOe}$

