

Demagnetization Curves of Ceramic Magnets

Tri-FER-8C

		SI	CGS
Remanence	Br	0.37 - 0.40 T	3.7 - 4.0 KG _s
Coercivity	H _{cb}	255 - 295 kA/m	3.2 - 3.7 KO _e
	H _{cj}	310 - 334 kA/m	3.9 - 4.2 KO _e
Maximum Energy Product	(BH) _{max}	25.5 - 30.3 kJ/m ³	3.2 - 3.8 MGO _e

