

Demagnetization Curves of Sintered Nd-Fe-B Magnets

Tri-Neo-44H

		SI	CGS
Remanence	Br	1.30 ~ 1.37 T	13.0 ~ 13.7 KG _s
Coercivity	H _{cb}	≥ 963 kA/m	≥ 12.1 KO _e
	H _{cj}	≥ 1273 kA/m	≥ 16 KO _e
Maximum Energy Product	(BH) _{max}	326 ~ 358 kJ/m ³	41 ~ 45 MGO _e

