

Demagnetization Curves of Sintered Nd-Fe-B Magnets

Tri-Neo-42SH

		SI	CGS
Remanence	Br	1.28 ~ 1.35 T	12.8 ~ 13.5 KGs
Coercivity	Hcb	≥ 955 kA/m	≥ 12.0 KOe
	Hcj	≥ 1512 kA/m	≥ 19 KOe
Maximum Energy Product	(BH)max	310 ~ 342 kJ/m ³	39 ~ 43 MGOe

