

Demagnetization Curves of Sintered Nd-Fe-B Magnets

Tri-Neo-38M

		SI	CGS
Remanence	Br	1.23 ~ 1.30 T	12.3 ~ 13.0 KG _s
Coercivity	H _{cb}	≥ 915 kA _m	≥ 11.5 KO _e
	H _{cj}	≥ 1114 kA _m	≥ 14 KO _e
Maximum Energy Product	(BH) _{max}	287 ~ 318 kJ _m ³	36 ~ 40 MGO _e

