

Demagnetization Curves of Sintered Nd-Fe-B Magnets

Tri-Neo-39SH

		SI	CGS
Remanence	Br	1.23 ~ 1.30 T	12.3 ~ 13.0 KGs
Coercivity	Hcb	≥ 923 kA/m	≥ 11.6 KOe
	Hcj	≥ 1592 kA/m	≥ 20 KOe
Maximum Energy Product	(BH)max	287 ~ 318 kJ/m ³	36 ~ 40 MGOe

