

## Demagnetization Curves of Sintered Nd-Fe-B Magnets

### Tri-Neo-45

		SI	CGS
Remanence	Br	1.32 ~ 1.38 T	13.2 ~ 13.8 KGs
Coercivity	Hcb	≥ 836 kA/m	≥ 10.5 KOe
	Hcj	≥ 875 kA/m	≥ 11 KOe
Maximum Energy Product	(BH)max	334 ~ 355 kJ/m <sup>3</sup>	42 ~ 46 MGOe

