

Demagnetization Curves of Cast AlNiCo Magnets

Tri-AlNiCo-8

		SI	CGS
Remanence	Br	$\geq 0.80 \text{ T}$	$\geq 8,000 \text{ G}_s$
Coercivity	Hcb	$\geq 110.0 \text{ kA}_m$	$\geq 1,380 \text{ O}_e$
Maximum Energy Product	(BH)max	$\geq 4.0 \text{ kJ}_m^3$	$\geq 5.0 \text{ MGO}_e$

