

## Demagnetization Curves of Ceramic Magnets

### Tri-FER-8E

		SI	CGS
Remanence	Br	0.36 - 0.38 T	3.6 - 3.8 KG <sub>s</sub>
Coercivity	H <sub>cb</sub>	271 - 295 K <sub>A</sub> /m	3.4 - 3.7 KO <sub>e</sub>
	H <sub>cj</sub>	382 - 406 K <sub>A</sub> /m	4.8 - 5.1 KO <sub>e</sub>
Maximum Energy Product	(BH) <sub>max</sub>	24.7 - 27.9 K <sub>J</sub> /m <sup>3</sup>	3.1 - 3.5 MGO <sub>e</sub>

