

## Demagnetization Curves of Sintered Nd-Fe-B Magnets

### Tri-Neo-33EH

		SI	CGS
Remanence	Br	1.14 ~ 1.22 T	11.4 ~ 12.2 KG <sub>s</sub>
Coercivity	H <sub>cb</sub>	≥ 851 kA/m	≥ 10.7 KO <sub>e</sub>
	H <sub>cj</sub>	≥ 2388 kA/m	≥ 30 KO <sub>e</sub>
Maximum Energy Product	(BH) <sub>max</sub>	247 ~ 279 kJ/m <sup>3</sup>	31 ~ 35 MGO <sub>e</sub>

