

Demagnetization Curves of Sintered Nd-Fe-B Magnets

Tri-Neo-35UH

		SI	CGS
Remanence	Br	1.18 ~ 1.25 T	11.8 ~ 12.5 KG _s
Coercivity	H _{cb}	≥ 875 kA/m	≥ 11.0 O _e
	H _{cj}	≥ 1989 kA/m	≥ 25 KO _e
Maximum Energy Product	(BH) _{max}	263 ~ 294 kJ/m ³	33 ~ 37 MGO _e

