

## Demagnetization Curves of Sintered Nd-Fe-B Magnets

### Tri-Neo-50

		SI	CGS
Remanence	Br	1.40 ~ 1.46 T	14.0 ~ 14.6 KGs
Coercivity	Hcb	≥ 835 kA/m	≥ 10.5 KOe
	Hcj	≥ 875 kA/m	≥ 11 KOe
Maximum Energy Product	(BH)max	374 ~ 406 kJ/m <sup>3</sup>	47 ~ 51 MGOe

