

Demagnetization Curves of Sintered AlNiCo Magnets

Tri-Sintered AlNiCo-5

		SI	CGS
Remanence	Br	$\geq 1.1 \text{ T}$	$\geq 11.0 \text{ KG}_s$
Coercivity	Hcb	$\geq 50.0 \text{ kA}_m$	$\geq 630 \text{ Oe}$
Maximum Energy Product	(BH)max	$\geq 34.0 \sim 38.0 \text{ kJ}_m^3$	$\geq 4.3 \sim 4.8 \text{ MGO}_e$

